

Augusta

	Unit	Test method	Tolerances
Deling Teilung Gauge	1/10 cut pile		
Breedte Breite Width	400/500	cm	CEN/TS 14159 ± 1%
Poolsamenstelling Polmaterial Pilecomposition	100% PP		
Totaal pool gewicht Gesamt poleinsatzgewicht Total pileweight	900	gr/m2	
Totaal gewicht Gesamtgewicht Total weight	1875 Ab/1915 Felt	gr/m2	ISO 8543 ±15%
Poolhoogte Polhöhe Pile height	6,5 (visual)	mm	ISO 1766
Totale hoogte Totale höhe Total height	8,5 Ab/ 9,5 Felt (visual)	mm	ISO 1765
Tuftdoek Träger Primary backing	Woven		
Aantal noppen Noppenzahl Stitches	161,540	1/m2	ISO 1763 -7.5% .+10%
Rug Rücken Backing	Ab/Felt		
Opmerkingen Bemerkungen Remarks			

Gut / Prodis: Ab: F55A0457 Felt 9DFE39BF



Reaction to fire Ef
Slip resistance: DS
EN 14041:2004
Z-156.601-676
Textile floor covering to
be used within a building



Condor Carpets b.v. • Randweg 14, 8061 RW Hasselt • The Netherlands
T +31 (0)38 477 89 11 • F +31 (0)38 477 89 22 • info@condorcarpets.nl

WWW.CONDORCOMPANY.EU