





UN38.3 TEST REPORT UN38.3 检测报告

Report No.:

报告编号:

CMC250703066

Name of Goods:

Lithium ion Battery

物品名称:

锂离子电池

Model:

型号:

POWERCUBE 2200

Type: 规格:

51.2V 42Ah 2150.4Wh

Client:

TURSAN NEW ENERGY(GUANG DONG) CO.,LTD.

委托单位:

拓芯安新能源(广东)有限公司

Classification

委托测试

of test: 检测类别:

Commission Test

Tested by 主检人:

Meiko Ma马方威

Approved by 批准人: (Technical Director 技术总监)

Barry He 何清

(Testing Engineer 测试工程师)

Meiko Ma 马方威

Inspected by 审核人:

Dylan Dou 霎 解記

Seal of CMC:

CMC 印章:

(Department Manager 部门经理)

Dylan Dou 窦明波

Date of Issue:

签发日期:

2025.07.30

CMC Testing International (Shenzhen) Co., Ltd.

众检检验认证 (深圳) 有限公司

1-3/F., Building 7, He'er Hongben Industrial Zone, Dawangshan Community, Shajing Subdistrict, Baoan District, Shenzhen, Guangdong, China 广东省深圳市宝安区沙井街道大王山社区和二鸿奔工业区7栋一层二层三层

400-1668-320 info@cmczj-lab.com www.cmczj-lab.com Version: A/3.1

1 / 18



TEST REPORT

检测报告

Name of Goods 物品名称	Lithium ion Ba 锂离子电池	ttery	Model 型号	POWERCUBE 2200		
Commissioner 委托单位		V ENERGY(GUANG (广东) 有限公司	G DONG) CO.,LTD.			
Commissioner's Address 委托单位地址		oad, Dalang Town, 大朗镇荔和路 68 号	Dongguan City, Gu	angdong Province,	China	
Manufacturer 制造商		V ENERGY(GUANG (广东) 有限公司	DONG) CO.,LTD.	(F	?)	
Manufacturer's Address 制造商地址	No. 68, Lihe Road, Dalang Town, Dongguan City, Guangdong Province, China 广东省东莞市大朗镇荔和路 68 号					
Manufacturer's			E-mail 邮箱	Tursan@turs	an-energy.com	
Contact Telephone 制造商联系电话	+86-769	9-81116886	Web 网址	www.tursan-energy.com		
Trade Mark/ identification 商标/识别码		Shape 形状	Cuboid 长方体	Size 尺寸 (L×W×T)	(491.2×230.1×29 6.3)mm	
Nominal Voltage 标称电压	51.2V	Charge Voltage 充电电压	58.4V	Rated Capacity 额定容量	42Ah	
Cell Model 电池型号	RF39-21A	Cell Nominal Voltage 电池标称电压	3.2V	Cell Rated Capacity 电池额定 <mark>容量</mark>	21Ah	
Cells Number 电池数量	32PCS	Sample Receiving Date 样品接收日期	2025.07.03	Testing Date 测试日期 2025.07.03 - 2025.07.24		
Test conclusion 检测结论	The sample has passed the test items of UNITED NATIONS "Manual of Tests and Criteria" ST/SG/AC.10/11/Rev.8 Subsection 38.3 经测试,该样品符合联合国《试验和标准手册》(第 8 修订版)38.3 标准要求。					

400-1668-320 info@cmczj-lab.com www.cmczj-lab.com 2 / 18



Test Standard 检测标准

UN "Manual of Tests and Criteria" ST/SG/AC.10/11/Rev.8 Subsection 38.3

联合国《试验和标准手册》(第8修订版)38.3节

Description and illustration of the sample: The sample's status is good.

样品说明及描述:样品状况良好。

Test item 检测项目	Sample No. 样品编号	State 状态	Remark 备注
T1,T2,T3,T4,T5	B001-B002	At first cycle, in fully charged states 第 1 个充电周期,完全充电状态	
T1,T2,T3,T4,T5	B003-B004	After 25 cycles ending in fully charged states 第 25 个充电周期,完全充电状态	-1
Т6	C001-C005	At first cycle at 50% of the design rated capacity 第 1 个充放电周期 50%设计额定容量状态	
Т6	C006-C010	After 25 cycle at 50% of the desig <mark>n rated capacity</mark> 第 25 个充放电周期 50%设计额定容量状态	-1
Т7	B005-B006	At first cycle, in fully charged states 第 1 个充电周期,完全充电状态	-1
Т7	B007-B008	After 25 cycles ending in fully charged states 第 25 个充电周期,完全充电状态	
Т8	C011-C020	At first cycle in fully discharged states 第 1 个充放电周期,完全放电状态	
Т8	C021-C030	After 25 cycles ending in fully discharged states 第 25 个 充放电周期,完全放电状态	

CXXX is used as the sample number of cells SN250703066CXXX, "X" is 0~9.

CXXX 代表电芯样板编号 SN250703066CXXX, X=0~9。

BXXX is used as the sample number of batteries SN250703066BXXX, "X" is 0~9

BXXX 代表电池包样板编号 SN250703066BXXX, X=0~9。

Description of the deviation from the standard, if any:

检测结果不符合标准项的说明:

Test environment conditions: Ambient temperature: 25°C±5°C, Ambient humidity: 45%-75%

检测环境条件: 环境温度: 25°C±5°C; 环境湿度: 45%-75%

Remarks:

备注:

1-3/F., Building 7, He'er Hongben Industrial Zone, Dawangshan Community, Shajing Subdistrict, Baoan District, Shenzhen, Guangdong, China 广东省深圳市宝安区沙井街道大王山社区和二鸿奔工业区 7 栋一层二层三层

400-1668-320 info@cmczj-lab.com www.cmczj-lab.com 3 / 18



		Report No., Civicz	.507 0500
	ST/SG/AC.10/11/Rev.8 Subsection	38.3	
Clause 章节	Requirements 标准要求	Result 测试结果	Verdict 判定
38.3.4	Procedure 检测步骤		
38.3.4.1	Test 1: Altitude simulation 检测 1: 高度模拟		
	Test cells and batteries shall be stored at a pressure of 11.6kF hours at ambient temperature (20±5°C). 将电池和电池组在温度为 20±5°C,大气压力为不大于 11.6kPa 时。		
	Requirements 标准要求: 1) Cells and batteries Mass loss limit reference: Table 38.3.1 样品质量损失限值参考:表 38.3.1 2) Open circuit voltage not less than 90%, The requirement relating to voltage is not applicable to test cells and batteries at full discharged states. 样品试验后开路电压应不低于试验前开路电压的 90%,此要求不适用于完全放完电的电池或电池组。 3) No leakage, no venting, no disassembly, no rupture and no fire. 样品(电池)应无渗漏、无排气、无解体、无破裂以及无起火现象的发生。	Test Samples: No leakage, no venting, no disassembly, no rupture and no fire. 样品: 无渗漏、无排气、无解体、无破裂以及无起火现象。 The data is shown in Test Table T.1 数据见表 T.1	Pass 合格
38.3.4.2	Test 2: Thermal test 检测 2: 温度试验 Test cells and batteries are to be stored for 电池和电池组存储条件如下: 1) For small cells and batteries: one temperature cycle: 72±2°	C (6h) ~ -40±2°C (6h)	

Test cells and batteries are to be stored for	
电池和电池组存储条件如下:	
1) For small cells and batteries: one temperature cycle: 72±2°C (6h) ~ -40±2°C (6h)	
对于小型电池和 <mark>电池组:一次温</mark> 度循环为 72±2°C (6h)~-40±2°C (6h)	
For large cells and batteries: one temperature cycle: 72±2°C (12h) ~ -40±2°C (12h)	
对于大型电池和 <mark>电池组:一次温</mark> 度循 <mark>环为 72±2°C (12h) ~ -40±2°C (12h)</mark>	
2) The maximum time interval between test temperature extremes is 30minutes.	
温度转换最大间隔时间为 30min。	
3) This procedure is to be repeated 10 times. 重复 10 次循环。	
4) after which all test cells and batteries are to be stored for 24 hours at ambient	Pass

temperature (20±5°C). 循环结束后, 电池和电池组在 20±5°C 的条件下搁置 24 小时。

Requirement 标准要求:

1) Cells and batteries Mass loss limit reference: Table 38.3.1 样品质量损失限值参考:表 38.3.1

2) Open circuit voltage not less than 90%, The requirement relating to voltage is not applicable to test cells and batteries at full discharged states.

样品试验后开路电压应不低于试验前开路电压的 90%,此要求不适用于完全放完电的电池和电池组。

3) No leakage, no venting, no disassembly, no rupture and no fire. 样品(电池)应无渗漏、无排气、无解体、无破裂以及无起火现象的发生。

Test Samples: No leakage, no venting, no disassembly, no rupture and no fire.

样品:无渗漏、无排气、无解体、无破裂以及无起火现象。

The data is shown in Test Table T.2 数据见表 T.2 Pass 合格

1-3/F., Building 7, He'er Hongben Industrial Zone, Dawangshan Community, Shajing Subdistrict, Baoan District, Shenzhen, Guangdong, China 广东省深圳市宝安区沙井街道大王山社区和二鸿奔工业区 7 栋一层二层三层

400-1668-320 info@cmczj-lab.com www.cmczj-lab.com 4 / 18



ST/SG/AC.10/11/Rev.8 Subsection 38.3					
Clause 章节	Requirements 标准要求	Result 测试结果	Verdict 判定		
38.3.4.3	Test 3: Vibration 检测 3: 振动 1) Cells and batteries are firmly secured to the platform of the 电池和电池组牢固地安装在振动台(的台面)上。 2) The vibration: a sinusoidal waveform with a logarithmic swe and back to 7Hz traversed in 15 minutes. 振动以正弦波形式,以 7Hz 增加至 200Hz,然后在减少回到 7线 15 分钟的对数前移传送。 3) For cells and small batteries: from 7Hz a peak acceleration 18Hz is reached. The amplitude is then maintained at 0.8mm the frequency increased until a peak acceleration of 8gn occur peak acceleration of 8gn is then maintained until the frequency 7于电池和小型电池: 从 7Hz 开始,以 1gn 的峰值加速度保持将振幅保持在 0.8mm(总偏移 1.6mm)并且频率增加到 200Hz. For large batteries: from 7Hz a peak acceleration of 1gn is ma reached. The amplitude is then maintained at 0.8mm (1.6mm frequency increased until a peak acceleration of 2gn occurs (a acceleration of 2gn is then maintained until the frequency is in 对于大型电池: 从 7Hz 开始,以 1gn 的峰值加速度保持不变,保持在 0.8mm(总偏移 1.6mm)并且频率增加直到出现 2gn 自然后保持 2gn 的峰值加速度,直到频率增加到 200Hz。 4) This cycle repeated 12 times for a total of 3 hours for each perpendicular mounting position of the cell. One of the direction perpendicular to the terminal face. 以振动的其中一个方向必须是垂直样品极性,对每个电池从三个次,每个方向 3 个小时,共 9 小时。 Requirements 标准要求: 1) Cells and batteries Mass loss limit reference: Table 38.3.1 样品质量损失限值参考:表 38.3.1 2) Open circuit voltage not less than 90%, The requirement relating to voltage is not applicable to test cells and batteries at full discharged states. 样品试验后开路电压应不低于试验前开路电压的 90%,此要求不适用于完全放完电的电池和电池组。 3) No leakage, no venting, no disassembly, no rupture and no fire. 样品(电池)应无渗漏、无排气、无解体、无破裂以及无起火现象的发生。	rep between 7Hz and 200Hz Hz 为一个循环,一个循环持 of 1gn is maintained until (1.6mm total excursion) and rs (approximately 50Hz). A ry is increased to 200Hz. 不变,直到达到 18Hz。然后 a 8gn 的峰值加速度(大约 intained until 18Hz is total excursion) and the approximately 25Hz). A peak creased to 200Hz. 直到达到 18Hz。然后将振幅 的峰值加速度(大约 25Hz)。 of three mutually ons of vibration must be	Pass 合格		

400-1668-320 info@cmczj-lab.com www.cmczj-lab.com 5 / 18



	ST/SG/AC.10/11/Rev.8 Subsection	38.3	
Clause 章节	Requirements 标准要求	Result 测试结果	Verdict 判定
38.3.4.4	Test 4: Shock 检测 4: 冲击 1) Test cells and batteries shall be secured to the testing mach 以稳固的托架固定住每个电池和电池组样品的全部配件表面。 2) Each cell shall be subjected to a half-sine shock of peak ac duration of 6 milliseconds. Large cells may be subjected to a hacceleration of 50gn and pulse duration of 11 milliseconds. 对每个电池以峰值为 150gn 的半正弦的加速度撞击,脉冲持续速度 50gn 和脉冲持续时间 11ms 的半正弦波冲击。 Small batteries shall be subjected to a half-sine shock of peak Acceleration(gn)= √(100850/mass), which is smaller) acceleration of 50gn which is smaller) and pulse dud pulse duration of 6 millisecond subjected to a half-sine of peak accelration of 11 milliseconds. 对每个电池以峰值为 150gn(或与√(100850/mass)中较小值)的半正弦的6ms,大型电池须经受最大加速度 50gn(或与√(100850/mass)中较小值)的半正弦的6ms,大型电池须经受最大加速度 50gn(或与√(100850/mass)中较小值)的半正弦的6ms,大型电池须经受最大加速度 50gn(或与√(100850/mass)中较小值)的半正弦的6ms,大型电池须经受量大加速度 50gn(或与√(100850/mass)中较小值)的半正弦的6ms,大型电池须经受量大加速度 50gn(或与√(100850/mass)中较小值)的半正弦的6ms,大型电池须经受量大加速度 50gn(或与√(100850/mass)中较小值)的半正弦的6ms,大型电池须经受量大加速度 50gn(或与√(100850/mass)中较小值)的半正弦的6ms,大型电池须径可以使用的6ms,大型电池须径可以使用的6ms,大型电池须径可以使用的6ms,大型电池须径可以使用的6ms,大型电池须径可以使用的6ms,大型电池须径可以使用的6ms,大型电池须径可以使用6ms,大型电池须径可以使用6ms,大型电池须径可以使用6ms,大型电池须径可以使用6ms,大型电池须径可以使用6ms,大型电池须径可以使用6ms,大型电池须径可以使用6ms,大型电池须径可以使用6ms,大型电池须径可以使用6ms,大型电池须径可以使用6ms,大型电池须径可以使用6ms,大型电池须径可以使用6ms,大型电池须径可以使用6ms,大型电池须径可以使用6ms,上面6ms,上	nine. celeration of 150g _n and pulse half-sine shock of peak 6ms,大型电池须经受最大加 acceleration of 150g _n (or not of Acceleration(g _n)= (\frac{30000}{mass}), ds, large batteries shall be h加速度撞击,脉冲持续 和脉冲持续时间 11ms 的半 e positive direction followed pendicular mounting	Pass 合格

400-1668-320 info@cmczj-lab.com www.cmczj-lab.com 6 / 18



	ST/SG/AC.10/11/Rev.8 Subsection	38.3					
Clause 章节	RequirementsResult标准要求测试结果						
38.3.4.5	Test 5: External Short Circuit 检测 5: 外部短路						
	1) The cell or battery to be tested shall be heated for a period of time necessary to reach a homogeneous stabilized temperature 57±4°C. 加热电池或电池组样品直到温度稳定在 57±4°C						
	 2) The cell or battery shall be subjected to a short circuit condition with a total external resistance of less than 0.1 ohm at 57±4°C, This short circuit condition is continued for a least one hour after the cell or battery external case temperature has returned to 57±4° 将样品正负极用小于 0.1Ω 的总电阻回路进行短路,样品的外表温度恢复到 57±4°C 之后持短路状态 1 小时以上。 3) The cell or battery must be observed for a further six hours for the test to be conclud 对电池或电池组必须进一步观察 6 个小时才能下结论。 						
	Requirements 标准要求: 1) Cells external temperature not exceed 170°C. 电池的最高表面温度应不超过 170°C。 2) No disassembly, no rupture and no fire during the test and within six hours after the test. 测试中与测试后 6 小时内无解体、无破裂、无起火。	Test Samples: No leakage, no venting, no disassembly, no rupture and no fire. 样品: 无渗漏、无排气、无解体、无破裂以及无起火现象。 The data is shown in Test Table T.5 数据见表 T.5					

38.3.4.6 Test 6: Impact / Crush

检测 6: 撞击/挤压

Impact (applicable to cylindrical cells not less than 18mm in diameter)

撞击(适用于直径不小于18毫米的圆柱形电池)

1) This test sample cell or component cell is to be placed on a flat smooth surface.

将试验样品用的电池或元件电池放在一个平坦光滑的平面上

2) A 15.8 mm diameter bar is to be placed across the center of the sample, A 9.1kg mass is to be dropped from a height of 61±2.5cm onto the sample.

将一直径为 15.8mm 的不锈钢圆棒横过电池中部放置后,将一质量为 9.1kg 的物体从 61±2.5cm 的高度落向样品。

3) The test sample is to be impacted with its longitudinal axis parallel to the flat surface and perpendicular to the longitudinal axis of the 15.8mm ± 0.1mm diameter curved surface lying across the center of the test sample. Each sample is to be subjected to only a single impact.

接受撞击的试样,纵轴应与平坦的表面平行并与横放在试样中心的直径 15.8±0.1 毫米弯曲表 面的纵轴垂直。每一个试样只经受一次撞击。

Requirements 标准要求:

1) Cells external temperature not exceed 170°C.

电池的最高表面温度应不超过 170°C。

2) No disassembly, no rupture and no fire during the test and within six hours after the test.

测试中与测试后 6 小时内无解体、无破裂、无起火。

Test Samples: No leakage, no venting, no disassembly, no rupture and no fire.

样品:无渗漏、无排气、无 解体、无破裂以及无起火现 象。

The data is shown in Test Table T.6 数据见表 T.6

Pass

合格

1-3/F., Building 7, He'er Hongben Industrial Zone, Dawangshan Community, Shajing Subdistrict, Baoan District, Shenzhen, Guangdong, China 广东省深圳市宝安区沙井街道大王山社区和二鸿奔工业区7栋一层二层三层

400-1668-320 info@cmczj-lab.com 7 / 18 www.cmczj-lab.com



ST/SG/AC.10/11/Rev.8 Subsection 38.3				
Clause 章节	Requirements 标准要求	Result 测试结果	Verdict 判定	
	Crush (applicable to prismatic, pouch, coin/button cells and cy in diameter). 挤压(适用于棱柱形、袋装、硬币/纽扣电池和直径小于 18 毫分 1) A cell or component cell is to be crushed between two flat s gradual with a speed of approximately 1.5cm/s at the first poin to be continued until the first of the three options below is reac 将电池或元件电池放在两个平面之间挤压,挤压力度逐渐加大,约为 1.5 厘米/秒。挤压持续进行,直到出现以下三种情况之一。(a) The applied force reaches 13kN ± 0.78kN. 施加的力达到 13 千牛顿±0.78 千牛顿。(b) The voltage of the cell drops by at least 100mV. 电池的电压下降至少 100 毫伏。(c) The cell is deformed by 50% or more of its original thickness 电池变形达原始厚度的 50%或以上。 2). A prismatic or pouch cell shall be crushed by applying the force on its flat cells, the crush force shall be applied perpendicular to the long 棱柱形或袋装电池应从最宽的一面施压。纽扣/硬币形电池应从应从与纵轴垂直的方向施压。 Requirements 标准要求: 1) Cells external temperature not exceed 170°C.电池的最高表面温度应不超过 170°C。 2) No disassembly, no rupture and no fire during the test and within six hours after the test.测试中与测试后 6 小时内无解体、无破裂、无起火。	K的圆柱形电池)。 urfaces. The crushing is to be at of contact. The crushing is ched. A 在第一个接触点上的速度大: ss. force to the widest side. A at surfaces. For cylindrical gitudinal axis.	N/A 不适用	

400-1668-320 info@cmczj-lab.com www.cmczj-lab.com 8 / 18



	ST/SG/AC.10/11/Rev.8 Subsection	38.3					
Clause 章节	Requirements 标准要求	Result 测试结果	Verdict 判定				
38.3.4.7	Test 7: Overcharge 检测 7: 过度充电						
	1) The charge current shall be twice the manufacturer's recommended maximum continuous charge current. 以制造商建议的最大持续充电电流的两倍对样品充电。 2) The minimum voltage of the test shall be as follows: 试验的最小电压如下: a) When the manufacturer's recommended charge voltage is not more than 18V, the minimum voltage of the test shall be the lesser of two times the maximum charge voltage of the battery or 22V. 制造商建议的充电电压不大于 18V 时,试验的最小电压应是电池组最大充电电压的两倍或22V 两者中的较小者。 b) when the manufacturer's recommended charge voltage is more than 18V, the minimum voltage of the test shall be 1.2 times the maximum charge voltage. 制造商建议的充电电压大于 18V 时,试验的最小电压应为最大充电电压的 1.2 倍。 3) Tests are to be conducted at ambient temperature 20±5°C, The duration of the test shall be 24 hours. 试验应在环境温度(20±5°C)下进行。进行试验的时间应为 24 小时。 Requirements 标准要求: No disassembly and no fire during the test and within seven days after the test. 试验过程中和试验后 7 天内无解体,无起火。 Test Samples: No leakage, no venting, no disassembly, no rupture and no fire. 样品: 无渗漏、无排气、无解体、无破裂以及无起火现象。 The data is shown in Test Table T.7						
38.3.4.8	Test 8: Forced discharge 检测 8: 强制放电						
	Each cell shall be forced discharged at ambient temperature to a 12V D.C. power supply at an initial current equal to the max specified by the manufacturer. 每个电池应在环境温度(20±5°C)下与 12V 直流电源串联在起大放电电流的条件下强制放电。 The specified discharge current is to be obtained by connecting appropriate size and rating in series with the test cell. Each cerfor a time interval (in hours) equal to its rated capacity divided ampere). 将适当大小和额定值的电阻负荷与试验电池串联,计算得出给约行强制放电,放电时间(小时)应等于其额定容量除以初始试验电 Requirements 标准要求: No disassembly and no fire during the test and within seven days after the test. 试验过程中和试验后 7 天内无解体,无起火。	imum discharge current 已始电流等于制造商给定的最 ng a resistive load of the ell shall be forced discharged by the initial test current (in 定的放电电流。对每个电池进	Pass 合格				

1-3/F., Building 7, He'er Hongben Industrial Zone, Dawangshan Community, Shajing Subdistrict, Baoan District, Shenzhen, Guangdong, China 广东省深圳市宝安区沙井街道大王山社区和二鸿奔工业区 7 栋一层二层三层

The data is shown in Test

Table T.8 数据见表 T.8

400-1668-320 info@cmczj-lab.com www.cmczj-lab.com 9 / 18



ST/SG/AC.10/11/Rev.8 Subsection 38.3

General terms and definitions 一般术语与定义

Table 38.3.1: Mass loss limit 表 38.3.1: 质量损失限值

Mass M of cell or battery	Mass loss limit
电池或电池组质量 M	质量损失限值
M < 1 g	0.5%
1 g ≤ M ≤ 75 g	0.2%
M > 75 g	0.1%

In order to quantify the mass loss, the following procedure is provided:

Mass loss (%) = $(M_1 - M_2)/M_1 \times 100$

质量损失的量化值,可用以下公式计算:

质量损失(%) = (M₁ - M₂)/M₁ × 100

Where M1 is the mass before the test and M2 is the mass after the test. When mass loss does not exceed the values in Table 38.3.1, it shall be considered as "no mass loss".

式中: M1 是试验前的质量, M2 是试验后的质量。如果质量损失不超过表 38.3.1 所列的数值, 应视为"无质量损失"。

Leakage means the visible escape of electrolyte or other material from a cell or battery or the loss of material (except battery casing, handling devices or labels) from a cell or battery such that the loss of mass exceeds the values in Table 38.3.1.

渗漏是指可以看到的电解液或者其他物质从电池<mark>或电池组中漏出,或电池或</mark>电池组中的物质损失(不包括电池外壳、搬运装置、或标签),质量损失超过表 **38.3.1** 所列的数值。

Venting means the release of excessive internal pressure from a cell or battery in a manner intended by design to preclude rupture or disassembly.

排气是指按设计方式释放电池或电池组内部过高的压力,防止其破裂或解体。

Disassembly means a vent or rupture where solid matter from any part of a cell or battery penetrates a wire mesh screen (annealed aluminium wire with a diameter of 0.25 mm and grid density of 6 to 7 wires per cm) placed 25 cm away from the cell or battery.

解体是指排气或破裂使<mark>电池或电池组任何部分的固体物质穿过</mark>放在<mark>离电池或</mark>电池 25 cm 处的丝网筛(直径 0.25 mm 的软铝丝,网格密度每<u>厘米 6 至 7 条铝</u>丝)。

Rupture means the mechanical failure of a cell container or battery case induced by an internal or external cause, resulting in exposure or spillage but not ejection of solid materials.

破裂是指内部或外部原因引起的电池容器或电池组外壳机械损坏,造成内装物暴露或溢出,但无固体喷射。

Fire means that flames are emitted from the test cell or battery.

起火是指试验电池或电池组有火焰冒出。

400-1668-320 info@cmczj-lab.com www.cmczj-lab.com 10 / 18



Test Data 检测数据

Table T.1 Altitude simulation (表 T.1) 高度模拟

Sample No. 样品编号	Before Mass 测试前 样品质量 (kg)	Before Voltage 测试前 开路电压 (V)	After Mass 测试后 样品质量 (kg)	After Voltage 测试后 开路电压 (V)	Mass Loss 质量损失 (%)	Residual OCV 剩余电压 (%)	Test Result 测试结果
B001	23.307	55.17	23.307	53.97	0.000	97.82	Pass/合格
B002	23.329	55.21	23.328	54.06	0.004	97.92	Pass/合格
B003	23.303	55.03	23.301	53.88	0.009	97.91	Pass/合格
B004	23.317	55.13	23.316	54.01	0.004	97.97	Pass/合格

Notes 注释:

After the test, there is no leakage, no venting, no disassembly, no rupture and no fire. And change ratio is not less than 90 %. 检测后,样品无渗漏、无排气、无解体、无破裂和无起火。电压比不小于 90 %。

Table T.2 Thermal test (表 T.2) 温度试验

Sample No. 样品编号	Before Mass 测试前 样品质量 (kg)	Before Voltage 测试前 开路电压 (V)	After Mass 测试后 样品质量 (kg)	After Voltage 测试后 开路电压 (V)	Mass Loss 质量损失 (%)	Residual OCV 剩余电压 (%)	Test Result 测试结果
B001	23.307	53.97	23.302	53.85	0.021	99.78	Pass/合格
B002	23.328	54.06	23.325	53.96	0.013	99.82	Pass/合格
B003	23.301	53.88	23.296	53.73	0.021	99.72	Pass/合格
B004	23.316	54.01	23.312	53.91	0.017	99.81	Pass/合格

Notes 注释:

After the test, there is no leakage, no venting, no disassembly, no rupture and no fire. And change ratio is not less than 90 %. 检测后,样品无渗漏、无排气、无解体、无破裂和无起火。电压比不小于 90 %。

1-3/F., Building 7, He'er Hongben Industrial Zone, Dawangshan Community, Shajing Subdistrict, Baoan District, Shenzhen, Guangdong, China 广东省深圳市宝安区沙井街道大王山社区和二鸿奔工业区 7 栋一层二层三层

400-1668-320 info@cmczj-lab.com www.cmczj-lab.com 11 / 18



Table T.3 Vibration (表 T.3) 振动

Report No.:	CMC250703066
-------------	--------------

Sample No. 样品编号	Before Mass 测试前 样品质量 (kg)	Before Voltage 测试前 开路电压 (V)	After Mass 测试后 样品质量 (kg)	After Voltage 测试后 开路电压 (V)	Mass Loss 质量损失 (%)	Residual OCV 剩余电压 (%)	Test Result 测试结果
B001	23.302	53.85	23.299	53.81	0.013	99.93	Pass/合格
B002	23.325	53.96	23.325	53.96	0.000	100.00	Pass/合格
B003	23.296	53.73	23.296	53.71	0.000	99.96	Pass/合格
B004	23.312	53.91	23.310	53.86	0.009	99.91	Pass/合格

Notes 注释:

After the test, there is no leakage, no venting, no disassembly, no rupture and no fire. And change ratio is not less than 90 %. 检测后,样品无渗漏、无排气、无解体、无破裂和无起火。电压比不小于 90 %。

Table T.4 Shock (表 T.4) 冲击

Sample No. 样品编号	Before Mass 测试前 样品质量 (kg)	Before Voltage 测试前 开路电压 (V)	After Mass 测试后 样品质量 (kg)	After Voltage 测试后 开路电压 (V)	Mass Loss 质量损失 (%)	Residual OCV 剩余电压 (%)	Test Result 测试结果
B001	23.299	53.81	23.298	53.76	0.004	99.91	Pass/合格
B002	23.325	53.96	23.323	53.88	0.009	99.85	Pass/合格
B003	23.296	53.71	23.296	53.67	0.000	99.93	Pass/合格
B004	23.310	53.86	23.310	53.86	0.000	100.00	Pass/合格

Notes 注释:

After the test, there is no leakage, no venting, no disassembly, no rupture and no fire. And change ratio is not less than 90 %. 检测后,样品无<mark>渗漏、无排气、</mark>无解<mark>体、无破裂和无起</mark>火。电压比不小于 90 %。

400-1668-320 info@cmczj-lab.com www.cmczj-lab.com 12 / 18



Table T.5 External short circuit (表 T.5) 外部短路

Sample No. 样品编号	Max. External Temperature 样品表面最高温度(°C)	Test Result 测试结果
B001	57.6	Pass/合格
B002	57.7	Pass/合格
B003	57.6	Pass/合格
B004	57.8	Pass/合格

Notes 注释:

Test sample external temperature does not exceed 170°C and there is no disassembly, no rupture and no fire during the test and within six hours after the test.

检测样品表面温度不超过 170°C, 检测中与检测后 6 小时内无解体、无破裂、无起火。

Table T.6 Impact (表 T.6) 撞击

Sample No. 样品编号	Max. External Temperature 样品表面最高温度(°C)	T <mark>est Re</mark> sult 测试结果
C001	33.4	Pass/合格
C002	32.4	Pass/合格
C003	32.1	Pass/合格
C004	34.5	Pass/合格
C005	32.5	Pass/合格
C006	33.3	Pass/合格
C007	31.8	Pass/合格
C008	32.6	Pass/合格
C009	31.7	Pass/合格
C010	33.2	Pass/合格

Notes 注释:

Test sample external temperature does not exceed 170°C and there is no disassembly, no rupture and no fire during the test and within six hours after the test.

检测样品表面温度不超过 170°C,检测中与检测后 6 小时内无解体、无破裂、无起火。

400-1668-320 info@cmczj-lab.com www.cmczj-lab.com 13 / 18



Table T.7 Overcharge (表 T.7) 过度充电

Report No.: CMC250703066

Sample No. 样品编号	Test Result 测试结果
B005	Pass/合格
B006	Pass/合格
B007	Pass/合格
B008	Pass/合格

Notes 注释:

There is no disassembly and no fire during the test and within seven days after the test. 样品在检测中和检测后 7 天内无解体、无起火。

Table T.8 Forced discharge (表 T.8) 强制放电

Sample No. 样品编号	Test Result 测试结果	Sample No. 样品编号	Test Result 测试结果
C011	Pass/合格	C021	Pass/合格
C012	Pass/合格	C022	Pass/合格
C013	Pass/合格	C023	Pass/合格
C014	Pass/合格	C024	Pass/合格
C015	Pass/合格	C025	Pass/合格
C016	Pass/合格	C026	Pass/合格
C017	Pass/合格	C027	Pass/合格
C018	Pass/合格	C028	Pass/合格
C019	Pass/合格	C029	Pass/合格
C020	Pass/合格	C030	Pass/合格

Notes 注释:


There is no disassembly and no fire during the test and within seven days after the test. 样品在检测中和检测后 7 天<mark>内无解体、无起火</mark>。

400-1668-320 info@cmczj-lab.com www.cmczj-lab.com 14 / 18



Photos of Samples

样品照片



Picture 1. Front view of battery 图片 1. 电池组前视图



Picture 2. Back view of battery 图片 2. 电池组后视图


1-3/F., Building 7, He'er Hongben Industrial Zone, Dawangshan Community, Shajing Subdistrict, Baoan District, Shenzhen, Guangdong, China 广东省深圳市宝安区沙井街道大王山社区和二鸿奔工业区 7 栋一层二层三层

400-1668-320 info@cmczj-lab.com www.cmczj-lab.com 15 / 18





Picture 3. Front view of cell 图片 3. 电池前视图



Picture 4. Back view of cell 图片 4. 电池后视图


1-3/F., Building 7, He'er Hongben Industrial Zone, Dawangshan Community, Shajing Subdistrict, Baoan District, Shenzhen, Guangdong, China 广东省深圳市宝安区沙井街道大王山社区和二鸿奔工业区 7 栋一层二层三层

400-1668-320 info@cmczj-lab.com www.cmczj-lab.com 16 / 18



POWERCUBE 2200	POWERCUBE 2200
Model Name	800W*2 Max
Recommended.PVModule	
PV[1]/[2]Input Voltage	12v~60V
Startup MPPT Voltage	18V
Max.PVInput Voltage	60V
PV[1]/[2]Input Current	25A Max Each
PV[1]/[2]Input Power	800w Max Each
Battery chargeInput Power	1600W Max
Inverter[1]/[2]Output Voltage	18V~55V
Inverter[1]/[2]Output Current	28A Max
EachInverter[1]/[2]Output Power	800W Max Each
Total Output Power	1600W Max
Peak Efficiency	98%
Battery pack parameters	
LiFePO4 Battery	51.2V (2150.4Wh/42Ah)
Max charge current	40A
Max work current	50A
Parallel Capability	1+4 redundant units(Ma
Communication	RS485, CAN
Overall undervisible	58.4V ±50mV
Overall under-voltage protection Cycle Life	43.2V ±50mV
Type of Enclosure	≥3000@25°C,70% EOL
Control Method	IP65
Charging operation	Mobile Application
Discharging operating temperature	0°C~55°C
RoHS CE FC X	-15°C~60°C

Picture 5. Label view 图片 5. 标签视图



400-1668-320 info@cmczj-lab.com www.cmczj-lab.com 17 / 18



Important

注意事项

- 1. The test report is invalid if it is not affixed the official seal of the laboratory to it. 检测报告无本实验室公章(或检验检测专用章)无效。
- 2. Copies of the test report without the official seal of the laboratory are invalid. 复制检测报告未重新加盖本实验室公章(或检验检测专用章)无效。
- 3. It is forbidden to copy the test report partially without the written approval of the laboratory. 未经本实验室书面批准不得部分复制检测报告。
- 4. The test report is invalid without the signatures of Approver, Reviewer and Testing engineer. 检测报告无检测、审核、批准人签名无效。
- 5. The test report is invalid if it is blotted out. 检测报告涂改无效。
- 6. Objections to the test report must be submitted to CMC Testing International (Shenzhen) Co., Ltd. within 15 days.
 - 对检测报告若有异议,应于收到报告之日起十<mark>五天内向众检检验认证(深</mark>圳)有限公司提出。
- 7. This report is only responsible for the test results of the tested samples, and the test results and related judgment conclusions only reflect the evaluation of the tested samples. For the report and the content can not be used for commercial advertising, the use of direct or indirect losses and all legal consequences, the company does not assume any economic and legal responsibility.
 - 本报告仅对所测样品<mark>的检测结果负责,检测结果及其相关</mark>判定结论仅反映对所测样品的评价。对于报告及 所载内容不能进行商业广告宣传使用,使用所产生的直接或间接损失及一切法律后果,本单位不承担任何 经济和法律责任。
- 8. As for the Verdict, "--" means "no need for judgment", "P" means "pass", "F" means "fail" and "N/A" means "not applicable".

判定栏中"--"表示 "不需要判定", "P"表示"通过", "F"表示"不通过", "N/A"表示"不适用"。

*** E<mark>nd of Report </mark>*** *** 报告结束 ***